

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problems Mailbox.**

THIS PAGE BLANK (USPTO)

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08G 63/91, C12P 1/00	A1	(11) International Publication Number: WO 97/27237 (43) International Publication Date: 31 July 1997 (31.07.97)
(21) International Application Number: PCT/DK97/00025 (22) International Filing Date: 20 January 1997 (20.01.97) (30) Priority Data: 0066/96 22 January 1996 (22.01.96) DK (71) Applicant (for all designated States except US): NOVO NORDISK A/S [DK/DK]; Novo Allé, DK-2880 Bagsværd (DK). (72) Inventors; and (75) Inventors/Applicants (for US only): RIEGELS, Martin [DE/DE]; (DE). KOCH, Rainhard [DE/DE]; (DE). PEDERSEN, Lars, Saaby [DK/DK]; Novo Nordisk a/s, Novo Allé, DK-2880 Bagsværd (DK). LUND, Henrik [DK/DK]; Novo Nordisk a/s, Novo Allé, DK-2880 Bagsværd (DK). (74) Common Representative: NOVO NORDISK A/S; Corporate Patents, Novo Allé, D-2880 Bagsværd (DK).	(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>	
(54) Title: ENZYMATIC HYDROLYSIS OF CYCLIC OLIGOMERS (57) Abstract The present invention relates to a process for enzymatic hydrolysis of cyclic oligomers of poly(ethylene terephthalate), which process comprises subjecting the cyclic oligomer to the action of one or more lipolytic and/or biopolyester hydrolytic enzyme(s).		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LJ	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

ENZYMATIC HYDROLYSIS OF CYCLIC OLIGOMERS

TECHNICAL FIELD

5

The present invention relates to a process for enzymatic hydrolysis of cyclic oligomers of poly(ethylene terephthalate), which process comprises subjecting the cyclic oligomer to the action of one or more carboxylic ester hydrolases.

10

BACKGROUND ART

Poly(ethylene terephthalate) fibers accounts for the main part of the polyester applied by the textile industry. The fibers
15 are produced by e.g. poly-condensation of terephthalic acid and ethylene glycol, and drawing of fibers from a melt. During these processes, at high temperatures, cyclic oligomers, in particular cyclic tri(ethylene terephthalate), are formed in and on the fibers.

20 Cyclic oligomers tend to give fabrics with a content of poly(ethylene terephthalate) fibers a grayish appearance. This is due to deposits of cyclic oligomers on the surface of the fabric, which is particularly outspoken after high temperature wet processes like HT (high temperature) dyeing. The cyclic
25 oligomers are difficult to remove and may even be resistant to an alkaline post treatment [cf. G. Valk et al.; Melliand Textilberichte 1970 5 504-508]. Therefore, to be effective, the alkaline treatment has to be severe, which results in a significant loss of fiber material. Also, organic extraction of
30 the cyclic oligomers is a technical possibility, but not industrially feasible.

SUMMARY OF THE INVENTION

35 It is an object of the present invention to provide an enzymatic process for removal of cyclic oligomers of poly(ethylene terephthalate), in particular cyclic tri(ethylene

terephthalate), by which process the cyclic oligomers are enzymatically hydrolyzed to linear fragments, which can then be removed under gentle conditions, or which may even be leftover. Thus the process of the invention avoids the need for harsh chemicals or organic extraction.

Accordingly, the invention provides a process for enzymatic hydrolysis of cyclic oligomers of poly(ethylene terephthalate), which process comprises subjecting the cyclic oligomer to the action of one or more carboxylic ester hydrolases.

DETAILED DISCLOSURE OF THE INVENTION

The present invention relates to a process for enzymatic hydrolysis of cyclic oligomers of poly(ethylene terephthalate). More specifically the invention provides a process for enzymatic hydrolysis of cyclic oligomers of poly(ethylene terephthalate), which process comprises subjecting the cyclic oligomer to the action of one or more carboxylic ester hydrolases, in particular lipolytic and/or biopolyester hydrolytic enzyme(s). In the context of this invention a biopolyester is a polyester of biological origin.

The process of the invention may in particular be applied to yarns or fabrics with a content of poly(ethylene terephthalate) fibers, during which process the content of cyclic oligomers, which were formed as byproducts during synthesis and processing of the fibers, becomes eliminated or at least significantly reduced.

30 Polyester Fabrics

Poly(ethylene terephthalate) is synthesized by condensation, drawn into fibers from a melt, possibly cut to stables, possibly mixed with other fiber types, and spun to yarn. The yarn is dyed and knitted into cloth or made into carpets, or the yarn is woven into fabric and dyed. These processes can be followed by finishing (post treatment) steps.

During synthesis and drawing, cyclic oligomers of poly(ethylene terephthalate) are formed on and in the fibers. These cyclic oligomers are partly deposited on machinery, partly staying on/in the fibers, which turns out to give an undesirable grayish appearance of the final fabric or carpet.

Cyclic oligomers can be removed by organic extraction, but such a process is not industrially feasible due to cost and problems in handling and regeneration of large quantities of organic solvents. Cyclic oligomers can also be removed by an alkaline post scouring step, but to be effective the alkaline treatment has to be severe and results in significant loss of fiber material, too.

According to the present invention, removal of cyclic oligomers, in particular cyclic trimers, can be accomplished by hydrolysis with one or more hydrolytic enzymes. The enzyme breaks the ring structure of the cyclic oligomer by hydrolyzing an ester bond. The resulting product creates less of a problem, because it can be removed under gentle conditions or even leftover in the product.

The enzymatic treatment does not have the disadvantages valid for organic extraction and alkaline post scouring, in particular it does not require large quantities of organic solvent to be involved, and there is no significant loss of fiber material.

The process of the invention is readily applicable in the textile industry as it can be carried out using existing wet processing apparatus, such as in a beam dyer, a Pad-Roll, a Jigger/Winch, a J-Box, or Pad-Steam types of apparatus. The process preferably takes place during the finishing (post treatment) step.

In a preferred embodiment the process of the invention may be accomplished on cyclic oligomers of poly(ethylene terephthalate) present on and/or in fibers or in yarn or fabric made (or partially made) from poly(ethylene terephthalate) fibers. Thus, the polyester yarn or fabric may be any yarn or fabric that is made from pure poly(ethylene terephthalate), or that is made from blends of poly(ethylene terephthalate) fibers

and any other material conventionally used for making yarns or fabrics.

Thus, in a preferred embodiment, the invention provides a process for enzymatic treatment of polyester fibers, which
5 process comprises subjecting the polyester fiber or fabric to the action of one or more carboxylic ester hydrolases, in particular lipolytic and/or biopolyester hydrolytic enzyme(s).

The polyester fabric may be any fabric or fabric blend comprising polyester. Preferably the fabric comprises more than
10 50% (w/w) of polyester, in particular more than 75% (w/w) of polyester, more than 90% (w/w) of polyester, or more than 95% (w/w) of polyester. In a most preferred embodiment, the process of the invention is applied to fabrics or textiles or yarns consisting essentially of poly(ethylene terephthalate) polyester
15 material, i.e. pure poly(ethylene terephthalate) polyester material.

Hydrolytic Enzymes

The enzymatic finishing process of the invention may be
20 accomplished using any carboxylic ester hydrolases, in particular lipolytic enzyme and/or any biopolyester hydrolytic enzyme. Such enzymes are well known and defined in the literature, cf. e.g. *Borgström B and Brockman H L, (Eds.); Lipases*; Elsevier Science Publishers B.V., 1984, and *Kolattukudy P E; The Biochemistry of*
25 *Plants*, Academic Press Inc., 1980 4 624-631.

In the context of this invention lipolytic enzymes include true lipases, esterases, phospholipases, and lyso-phospholipases. More specifically the lipolytic enzyme may be a lipase as classified by EC 3.1.1.3, EC 3.1.1.23 and/or EC
30 3.1.1.26, an esterase as classified by EC 3.1.1.1, EC 3.1.1.2, EC 3.1.1.6, EC 3.1.1.7, and/or EC 3.1.1.8, a phospholipase as classified by EC 3.1.1.4 and/or EC 3.1.1.32, and a lyso-phospholipase as classified by EC 3.1.1.5.

The lipolytic enzyme preferably is of microbial origin,
35 in particular of bacterial, of fungal or of yeast origin.

In a particular embodiment, the lipolytic enzyme used may be derived from a strain of *Absidia*, in particular *Absidia*

blakesleena and Absidia corymbifera, a strain of Achromobacter, in particular Achromobacter iophagus, a strain of Aeromonas, a strain of Alternaria, in particular Alternaria brassiciola, a strain of Aspergillus, in particular Aspergillus niger and 5 Aspergillus flavus, a strain of Achromobacter, in particular Achromobacter iophagus, a strain of Aureobasidium, in particular Aureobasidium pullulans, a strain of Bacillus, in particular Bacillus pumilus, Bacillus strearothermophilus and Bacillus subtilis, a strain of Beauveria, a strain of Brochothrix, in 10 particular Brochothrix thermosohata, a strain of Candida, in particular Candida cylindracea (Candida rugosa), Candida paralipolytica, and Candida antarctica, a strain of Chromobacter, in particular Chromobacter viscosum, a strain of Coprinus, in particular Coprinus cinerius, a strain of Fusarium, in particular 15 Fusarium oxysporum, Fusarium solani, Fusarium solani pisi, and Fusarium roseum culmorum, a strain of Geotricum, in particular Geotricum penicillatum, a strain of Hansenula, in particular Hansenula anomala, a strain of Humicola, in particular Humicola brevispora, Humicola brevis var. thermoidea, and Humicola 20 insolens, a strain of Hyphozyma, a strain of Lactobacillus, in particular Lactobacillus curvatus, a strain of Metarhizium, a strain of Mucor, a strain of Paecilomyces, a strain of Penicillium, in particular Penicillium cyclopium, Penicillium crustosum and Penicillium expansum, a strain of Pseudomonas in 25 particular Pseudomonas aeruginosa, Pseudomonas alcaligenes, Pseudomonas cepacia (syn. Burkholderia cepacia), Pseudomonas fluorescens, Pseudomonas fragi, Pseudomonas maltophilia, Pseudomonas mendocina, Pseudomonas mephitica lipolytica, Pseudomonas alcaligenes, Pseudomonas plantari, Pseudomonas 30 pseudoalcaligenes, Pseudomonas putida, Pseudomonas stutzeri, and Pseudomonas wisconsinensis, a strain of Rhizoctonia, in particular Rhizoctonia solani, a strain of Rhizomucor, in particular Rhizomucor miehei, a strain of Rhizopus, in particular

Rhizopus japonicus, *Rhizopus microsporus* and *Rhizopus nodosus*, a strain of *Rhodosporidium*, in particular *Rhodosporidium toruloides*, a strain of *Rhodotorula*, in particular *Rhodotorula glutinis*, a strain of *Sporobolomyces*, in particular
5 *Sporobolomyces shibatanus*, a strain of *Thermomyces*, in particular *Thermomyces lanuginosus* (formerly *Humicola lanuginosa*), a strain of *Thiarosporella*, in particular *Thiarosporella phaseolina*, a strain of *Trichoderma*, in particular *Trichoderma harzianum*, and *Trichoderma reesei*, and/or a strain of *Verticillium*.

10 In a more preferred embodiment, the lipolytic enzyme used according to the invention is derived from a strain of *Aspergillus*, a strain of *Achromobacter*, a strain of *Bacillus*, a strain of *Candida*, a strain of *Chromobacter*, a strain of *Fusarium*, a strain of *Humicola*, a strain of *Hyphozyma*, a strain
15 of *Pseudomonas*, a strain of *Rhizomucor*, a strain of *Rhizopus*, or a strain of *Thermomyces*.

In a more preferred embodiment, the lipolytic enzyme used according to the invention is derived from a strain of *Bacillus pumilus*, a strain of *Bacillus stearothermophilus* a strain of
20 *Candida cylindracea*, a strain of *Candida antarctica*, in particular *Candida antarctica* Lipase B (obtained as described in WO 88/02775), a strain of *Humicola insolens*, a strain of *Hyphozyma*, a strain of *Pseudomonas cepacia*, or a strain of *Thermomyces lanuginosus*.

25 In the context of this invention biopolyester hydrolytic enzyme include esterases and poly-hydroxyalkanoate depolymerases, in particular poly-3-hydroxyalkanoate depolymerases. In fact an esterase is a lipolytic enzyme as well as a biopolyester hydrolytic enzyme.

30 In a more preferred embodiment, the esterase is a cutinase or a suberinase. Also in the context of this invention, a cutinase is an enzyme capable of degrading cutin, cf. e.g. Lin T S & Kolattukudy P E, J. Bacteriol. 1978 133 (2) 942-951, a suberinase is an enzyme capable of degrading suberin, cf. e.g. ,

Kolattukudy P E; Science 1980 208 990-1000, Lin T S & Kolattukudy P E; Physiol. Plant Pathol. 1980 17 1-15, and The Biochemistry of Plants, Academic Press, 1980 Vol. 4 624-634, and a poly-3-hydroxyalkanoate depolymerase is an enzyme capable of
5 degrading poly-3-hydroxyalkanoate, cf. e.g. Foster et al., FEMS Microbiol. Lett. 1994 118 279-282. Cutinases, for instance, differs from classical lipases in that no measurable activation around the critical micelle concentration (CMC) of the tributyrine substrate is observed. Also, cutinases are considered
10 belonging to a class of serine esterases.

The biopolyester hydrolytic enzyme preferably is of microbial origin, in particular of bacterial, of fungal or of yeast origin.

In a preferred embodiment, the biopolyester hydrolytic
15 enzyme is derived from a strain of *Aspergillus*, in particular *Aspergillus oryzae*, a strain of *Alternaria*, in particular *Alternaria brassiciola*, a strain of *Fusarium*, in particular *Fusarium solani*, *Fusarium solani pisi*, *Fusarium roseum culmorum*, or *Fusarium roseum sambucium*, a strain of *Helminthosporum*, in
20 particular *Helminthosporum sativum*, a strain of *Humicola*, in particular *Humicola insolens*, a strain of *Pseudomonas*, in particular *Pseudomonas mendocina*, or *Pseudomonas putida*, a strain of *Rhizoctonia*, in particular *Rhizoctonia solani*, a strain of *Streptomyces*, in particular *Streptomyces scabies*, or a strain of
25 *Ulocladium*, in particular *Ulocladium consortiale*. In a most preferred embodiment the biopolyester hydrolytic enzyme is a cutinase derived from a strain of *Humicola insolens*, in particular the strain *Humicola insolens* DSM 1800.

In another preferred embodiment, the poly-3-
30 hydroxyalkanoate depolymerase is derived from a strain of *Alcaligenes*, in particular *Alcaligenes faecalis*, a strain of *Bacillus*, in particular *Bacillus megaterium*, a strain of *Camomonas*, in particular *Camomonas testosteroni*, a strain of *Penicillium*, in particular *Penicillium funiculosum*, a strain of
35 *Pseudomonas*, in particular *Pseudomonas fluorescens*, *Pseudomonas*

lemoinei and *Pseudomonas oleovorans*, or a strain of *Rhodospirillum*, in particular *Thodospirillum rubrum*.

Process Conditions

5 The enzymatic treatment according to the present invention preferably is carried out as a wet process. It is at present contemplated that a suitable liquor:textile ratio may be in the range of from about 20:1 to about 1:1, preferentially in the range of from about 15:1 to about 5:1.

10 Enzyme dosage must be a function of the enzyme(s) applied and the reaction time and conditions given. It is at present contemplated that the enzyme(s) may be dosed in a total amount of from about 0.001 g/kg to about 5 g/kg enzyme per yarn or fabric, preferably from about 0.001 g/kg to about 0.5 g/kg.

15 The enzymatic hydrolysis may be carried out in the temperature range of from about 30°C to about 100°C, preferentially from about 50°C to about 100°C. The pH range may, dependent on the enzyme(s) applied, be from about pH 4 to pH 11. It is at present contemplated that a suitable reaction time may
20 be in the range of from about 15 minutes to about 3 hours.

 The process of the invention may further comprise the addition of one or more chemicals capable of improving the enzyme-substrate interaction (in order to improve the substrate's accessibility and/or dissolve reaction products),
25 which chemicals may be added prior to, or simultaneously with the enzymatic treatment. Such chemicals may in particular be surfactants, wetting agents, and dispersing agents, or mixtures hereof.

 The process of the invention may optionally comprise a
30 rinsing step during which the hydrolyzed cyclic oligomers are subjected to rinsing, in particular to rinsing with dilute alkali. Dilute alkali dissolves linear fragments of the cyclic oligomers, and may to some extent further hydrolyze these linear fragments.

35 In the context of this invention dilute alkali comprise aqueous solutions having a pH in the range of from about pH 7 to about pH 11, more preferably of from about pH 7 to about pH 10,

most preferred of from about pH 7 to about pH 9. A buffer may be added to the medium.

EXAMPLES

5

The invention is further illustrated in the following examples, which are not intended to be in any way limiting to the scope of the invention as claimed.

10

EXAMPLE 1

In this example eleven different enzymes with lipolytic and/or biopolyester hydrolytic activity are examined for their activity towards cyclic oligomers of poly(ethylene terephthalate). The cyclic oligomers are obtained from polyester fabric by Soxhlet extraction with 1,4-dioxane.

The eleven enzymes tested in this example are:

Bacillus pumilus lipase (obtained as described in WO 91/16422);

20 *Bacillus stearothermophilus* lipase (obtained as described in JP 64/744992);

Candida antarctica Lipase B (obtained as described in WO 88/02775);

25 *Candida cylindracea* (= *Candida rugosa*) lipase (obtained from Nippon Oil & Fats Co. Ltd., Japan);

Pseudomonas cepacia lipase (obtained as described in EP 331,376);

Glucosaminated Lipolase™ (obtained as described in WO 95/09909);

30 *Thermomyces lanuginosus* (formerly *Humicola lanuginosa*) lipase (obtained as described in EP 305,216);

Recombinantly produced guinea pig lipase (rGPL) (obtained as described in WO 93/00426);

35 *Humicola insolens* cutinase (actually a lipase also having cutinase activity, obtained from the strain *Humicola*

insolens DSM 1800 as described in Example 2 of US 4,810,414);

Aspergillus aculeatus pectin methyl esterase (PME; obtained as described in WO 94/25575); and

5 *Aspergillus aculeatus* acetyl esterase (AE; obtained as described in WO 95/02689).

The substrate solution is incubated with the hydrolytic enzyme preparation in an agar gel containing phenol-red. 1000 ml agar gel is prepared from 17 g Agarose type 2 medium EEO (Sigma, 10 A-6877), 3 g NaNO₃, 1 g K₂HPO₄, 0.5 g KCl, 1 ml 1% (w/v) FeSO₄, and 50 ml 0.4 g/l phenol-red solution, pH adjusted to 8.0-8.5.

Table 1
Clarification Zones

15

Strain	Enzyme type	Activity on tributyrine	Activity on cyclic oligo.
Blank		0	0
<i>Bacillus pumilus</i> lipase	Bacterial lipase	3	1
<i>Bacillus stearothermophilus</i> lipase	Bacterial lipase	3-4	1
<i>Candida antarctica</i> Lipase B	Fungal lipase	3	0-1
<i>Candida cylindracea</i> (rugosa) lipase	Fungal lipase	4	0-1
<i>Pseudomonas cepacia</i> lipase	Fungal lipase	5	1
<i>Thermomyces lanuginosus</i> lipase	Fungal lipase	4	1
Glucosaminated Lipolase™	Mod. Fungal lipase	3	0-1
Recombinant guinea pig lipase	Rec. Mammal lipase	4	2

<i>Humicola insolens</i> cutinase	Fungal cutin esterase	4	1
<i>Aspergillus</i> <i>aculeatus</i> PME	Fungal pectin methyl esterase	0	0-1
<i>Aspergillus</i> <i>aculeatus</i> AE	Fungal acetyl esterase	0	1

The substrate solution, 15 μ l tributyrine or cyclic oligomers, is poured into plug holes in the agar, and the aqueous enzyme solution is mixed into the substrate solution. If the enzyme is capable of hydrolyzing the substrate, then acids are formed and diffuse into the gel, where the pH indicator phenol-red turns from red to yellow.

10

EXAMPLE 2

In this example a lipolytic and biopolyester hydrolytic enzyme (*Humicola insolens* cutinase derived from the strain *Humicola insolens* DSM 1800 as described in WO 96/13580) is examined for activity towards cyclic tri(ethylene terephthalate). The cyclic trimer is obtained from polyester fabric by Soxhlet extraction with 1,4-dioxane, and is further purified by ethanol and 1,4-dioxane washes.

A mixture of the following composition is incubated at 30°C for 16 hours:

0.25 ml glycylglycine buffer, 0.2 M pH 8.5
2.50 ml de-ionized water
0.25 ml cyclic trimer, 5.0 mM in 1,4-dioxane
62.5 μ g of enzyme

25

The reaction is stopped by adding 5.0 ml 1,4-dioxane, and the mixture is analyzed on a reverse phase HPLC, ODS (octa dodecyl silicate) column eluted with acetonitrile and pH 3.0 phosphate-buffer. Detection of the reaction products is carried out spectrophotometrically at 240 nm, at which wavelength the terephthalic acid and terephthalate derivatives adsorb.

30

Table 2
Reaction Products as Determined by HPLC

Peak Area, 240 nm	Blank	<i>Humicula insolens</i> cutinase
Cyclic trimer (17.6 min.)	8.07 (100%)	3.69 (44%)
Product 1 (3.8 min.)	0.00 (0%)	Trace (<5%)
Product 2 (4.5 min.)	0.00 (0%)	2.26 (27%)
Product 3 (5.3 min.)	0.00 (0%)	Trace (<5%)
Product 4 (13.0 min.)	0.00 (0%)	2.40 (29%)
Total area, 240 nm	8.07	8.35

5

In this example 56% of the cyclic tri(ethylene terephthalate) is degraded under the given conditions by the cutinase from *Humicula insolens*, yielding four detectable degradation products.

10 Following this experiment three of these products have been identified as ethylene bis(terephthalic acid) ester (MW=342), terephthalic acid mono(2-hydroxyethyl) ester (MW=210) and terephthalic acid (MW=166).

CLAIMS

1. A process for enzymatic hydrolysis of cyclic oligomers of poly(ethylene terephthalate), which process comprises
5 subjecting the cyclic oligomer to the action of one or more carboxylic ester hydrolases.
2. The process according to claim 1, which process comprises
10 subjecting the cyclic oligomer to the action of one or more lipolytic and/or biopolyester hydrolytic enzyme(s).
3. The process according to claim 2, wherein the lipolytic
15 enzyme is a lipase, an esterase, a phospholipase, and/or a lyso-phospholipase.
4. The process according to claim 3, wherein the lipolytic
20 enzyme is a lipase derived from a strain of *Aspergillus*, a strain of *Achromobacter*, a strain of *Bacillus*, a strain of *Candida*, a strain of *Chromobacter*, a strain of *Fusarium*, a strain of *Humicola*, a strain of *Hyphozyma*, a strain of *Pseudomonas*, a strain of *Rhizomucor*, a strain of *Rhizopus*, or a strain of *Thermomyces*.
5. The process according to claim 4, wherein the lipolytic
25 enzyme is a lipase derived from a strain of *Bacillus pumilus*, a strain of *Bacillus stearothermophilus*, a strain of *Candida cylindracea*, a strain of *Candida antarctica*, a strain of *Humicola insolens*, a strain of *Hyphozyma*, a strain of *Pseudomonas cepacia*, or a strain of *Thermomyces lanuginosus*.
6. The process according to claim 2, wherein the lipolytic
30 enzyme is a phospholipase or lyso-phospholipase derived from a strain of *Achromobacter*, in particular a *Achromobacter iophagus*, a strain of *Candida*, in particular *Candida paralipolytica*, a strain of *Pseudomonas*, in particular
35 *Pseudomonas mephitica lipolytica*.

7. The process according to claim 2, wherein the biopolyester hydrolytic enzyme is an esterase and/or poly-hydroxyalkanoate depolymerase.
- 5
8. The process according to claim 7, wherein the esterase is a cutinase, or a suberinase.
9. The process according to claim 7, wherein the esterase is
10 derived from a strain of *Aspergillus*, in particular *Aspergillus oryzae*, a strain of *Alternaria*, in particular *Alternaria brassiciola*, a strain of *Fusarium*, in particular *Fusarium solani*, *Fusarium solani pisi*, *Fusarium roseum culmorum*, or *Fusarium roseum sambucium*, a strain of
15 *Helminthosporium*, in particular *Helminthosporium sativum*, a strain of *Humicola*, in particular *Humicola insolens*, a strain of *Pseudomonas*, in particular *Pseudomonas mendocina*, or *Pseudomonas putida*, a strain of *Rhizoctonia*, in particular *Rhizoctonia solani*, a strain of *Streptomyces*, in particular
20 *Streptomyces scabies*, or a strain of *Ulocladium*, in particular *Ulocladium consortiale*.
10. The process according to claim 9, wherein the esterase is a cutinase derived from a strain of *Humicola insolens*, in
25 particular the strain *Humicola insolens* DSM 1800.
11. The process according to claim 7, wherein the poly-hydroxyalkanoate depolymerase is derived from a strain of *Alcaligenes*, in particular *Alcaligenes faecalis*, a strain of
30 *Bacillus*, in particular *Bacillus megaterium*, a strain of *Camomonas*, in particular *Camomonas testosteroni*, a strain of *Penicillium*, in particular *Penicillium funiculosum*, a strain of *Pseudomonas*, in particular *Pseudomonas fluorescens*, *Pseudomonas lemoignei* and *Pseudomonas oleovorans*, or a strain
35 of *Rhodospirillum*, in particular *Thodospirillum rubrum*.

12. The process according to any of claims 1-11, further comprising the addition of one or more chemicals improving the enzyme-substrate interaction, in particular a surfactants, a wetting agent, and/or a dispersing agent.

13. The process according to any of claims 1-12, wherein the enzymatic action is followed by a rinsing step, during which step hydrolyzed cyclic oligomer is subjected to treatment with an alkaline solution.

14. The process according to either of claims 1-13, wherein the cyclic oligomer is present in and on the fibers of a polyester containing fabric or yarn.

15. The process according to either of claims 1-14, in which the cyclic oligomer is cyclic tri(ethylene terephthalate).

INTERNATIONAL SEARCH REPORT

International application No.
PCT/DK 97/00025

A. CLASSIFICATION OF SUBJECT MATTER		
IPC6: C08G 63/91, C12P 1/00 According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols)		
IPC6: C08G, C12P		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
SE,DK,FI,NO classes as above		
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
REG, CAPLUS, WPI, DPCI, SCISEARCH		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	STN International, File CAPLUS, CAPLUS accession no. 1982:7275, Teijin Ltd: "Partial hydrolysis of polyesters", JP,A2,56118420, 810917, Showa	1-15
	--	
A	US 4362852 A (DAVID PENDLEBURY ET AL), 7 December 1982 (07.12.82)	1-15
	--	
A	Journal of Applied Polymer Science, Volume 32, 1986, A.L. Cimecioglu et al, "Properties of Oligomers Present in Poly(ethylene Terephthalate)"	1-15
	--	

<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input checked="" type="checkbox"/> See patent family annex.		
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family		
Date of the actual completion of the international search		Date of mailing of the international search report
25 April 1997		06 -05- 1997
Name and mailing address of the ISA/ Swedish Patent Office Box 5055, S-102 42 STOCKHOLM Facsimile No. +46 8 666 02 86		Authorized officer Carolina Gómez Lagerlöf Telephone No. +46 8 782 25 00

Information on patent family members

PCT/DK 97/00025

Form PCT/ISA/210 (patent family annex) (July 1992)

THIS PAGE BLANK (USPTO)